

FIBERMIX

HIGH STRENGTH STRUCTURAL STEEL FIBRE FOR CONCRETE REINFORCEMENT



DRACO

CONCRETE
line

FIBRE TO REINFORCE
CONCRETE



FIBERMIX is a low carbon structural steel fibre that gives concrete high ductility and mechanical impact strength. The particular shape of the fibre ensures high anchorage in the cement matrix.

ADVANTAGES

The physical and mechanical properties and special geometry make **FIBERMIX** the ideal solution for mortar and concrete reinforcement.

FIBERMIX gives concrete:

- ✓ High impact resistance
- ✓ High ductility and toughness of the structure
- ✓ High resistance to fatigue and dynamic loads
- ✓ Improved post-breakdown behaviour
- ✓ Excellent crack control
- ✓ Quick and easy application without special equipment
- ✓ Homogeneous distribution throughout the concrete mass
- ✓ Possibility of replacing the main reinforcement in flooring
- ✓ Partial replacement of secondary reinforcement.



APPLICATION

FIBERMIX improves the post-cracking tensile behaviour of concrete mixes and is particularly used in the following applications:

- ✓ Industrial flooring in concrete
- ✓ Prefabricated structural element
- ✓ Parking areas, airport runways, storage areas
- ✓ Casting of structures subject to high static and dynamic loads
- ✓ Casting of decks, slabs and thin-section structures
- ✓ Hydraulic works
- ✓ Shrinkage-compensated mortars
- ✓ Anti-seismic systems.



© Copyright 2012 - All rights reserved - The information provided in this data sheet corresponds accurately and truthfully to our best current knowledge - Differences may be encountered depending on how accurately the various stages of installation are carried out, for which we bear no responsibility. Our warranty is, therefore, limited to the quality and consistency of the product supplied as per the indicators set out in this document. This edition supersedes and replaces the previous editions.

APPLICATION

- ▶ Place all the mix components (aggregates, water, cement and admixtures) in the concrete mixer and with the mixer rotating at high speed gradually add fibres until the desired dosage is reached.
- ▶ Continue mixing for at least 5 minutes to ensure even distribution.

PACKAGING AND STORAGE

FIBERMIX is supplied in 25 kg boxes on 1200 kg pallets.
Store pallets safe from exposure to bad weather.

YIELD

The dosage of **FIBERMIX** is chosen according to the characteristics desired for the structure, and this depends on the type and stresses to which it will be subjected.

Typically, the dosage ranges from 30 to 70 kg/m³ of concrete.

PRODUCT CHARACTERISTICS AND PERFORMANCE

COMPOSITION	High strength, low carbon steel
LENGTH	50 mm
EQUIVALENT DIAMETER	1 mm
ASPECT RATIO (L/D)	50
SHAPE	Hooked at the end
TYPE	Loose
TENSILE STRENGTH (R _m)	1180 MPa
FIBRE WEIGHT (G/EACH)	0.3266
NO. OF FIBRES PER KG	3087
DIMENSIONAL TOLERANCES	
EQUIVALENT LENGTH AND DIAMETER	± 10%
ASPECT RATIOS (L/D)	± 15%

Legal notes – SLCMP version of 01.03.2017

For the values and technical data in this Data Sheet, Draco Italiana s.p.a. adopts the parameters shown in the Data Sheet with the relative standards of reference. The Customer is required to verify that this sheet and the values shown are valid for the batch of the product of interest, and are not exceeded as they are replaced by subsequent editions. In the event of any uncertainty, compare the technical data sheet with the version in effect at the time the sales contract was concluded (available from the website www.draco-edilizia.it, and/or our Technical Office). In the event the Customer requests that our personnel provide any additional advice concerning the use of the product, such information, whether in verbal or written form, shall not constitute an additional obligation with respect to the terms of the purchase contract, and shall not, in any way, represent a contractual obligation on our part. Such information is based on our experience and is limited to the current state of practical and/or scientific knowledge; hence, it is not binding either for the customer or for the personnel assigned to apply the product. In particular, the Customer is required to check that our products are suitable for the intended use and application, and shall accept sole responsibility for any choices and decisions made on the basis of such checks.